

Listing of Claims:

1. (Original) A homo- or copolyoxymethylene containing the structural unit of formula I



where A is a radical derived from a homo- or copolyoxymethylene,

R¹ is an alkylene radical having at least two carbon atoms, or a cycloalkylene radical,

R² is a direct carbon-carbon bond, or an alkylene, cycloalkylene, arylene, or aralkylene radical, and

m is 0 or 1.


2. (Original) The homo- or copolyoxymethylene as claimed in claim 1, wherein m is 0.

3. (Original) The homo- or copolyoxymethylene as claimed in claim 1, wherein R¹ is a radical of the formula -C_nH_{2n}·, where n is a whole number from 2 to 6.

4. (Original) The homo- or copolyoxymethylene as claimed in claim 3, wherein R¹ is -CH₂-CH₂·.

5. (Currently Amended) The homo- or copolyoxymethylene as claimed in claim 1, wherein the polyoxymethylene radical A has from 99.9 to 90 mol% of repeat structural units of the formula -(CH₂-O)-x, where x is a whole number from 100 to 10,000, and from 0.1 to 10 mol% of repeat structural units which derive from ethylene oxide, from propylene 1,2-oxide, from butylene 1,2-oxide, from butylene 1,3-oxide, from 1,3-dioxane, from 1,3-dioxolane, from 1,3-dioxepan, from 1,3,6-trioxocane, and/or from linear oligo- or polyformals.

6. (Currently Amended) The homo- or copolyoxymethylene as claimed in claim 1, wherein the polyoxymethylene radical A has from 99.9 to 90 mol% of repeat structural units of the formula $-(CH_2-O)_x$, where x is a whole number from 100 to 10,000, and from 0.1 to 10 mol% of repeat structural units of the formula



where z is a whole number which is at least 1.

7. (Previously Presented) The homo- or copolyoxymethylene as claimed in claim 1, wherein the structural elements of the formula $-O-CO-(R^2-CO-)_m-O-$ derive from chain-linking agents which are selected from the group consisting of derivatives of carbonic acid or activated urea derivatives, or from esters or half-esters of dicarboxylic acids, or from dianhydrides of tetracarboxylic acids, or from mixtures of two or more of these compounds.

8. (Previously Presented) The homo- or copolyoxymethylene as claimed in claim 7, wherein the structural elements of the formula $-O-CO-(R^2-CO-)_m-O-$ derive from diesters of carbonic acid.

9. (Original) The homo- or copolyoxymethylene as claimed in claim 7, wherein the structural elements of the formula $-O-CO-(R^2-CO-)_m-O-$ derive from diesters of oxalic acid, of the aromatic dicarboxylic acids, and/or of the aliphatic dicarboxylic acids.

10. (Original) The homo- or copolyoxymethylene as claimed in claim 9, wherein the structural elements of the formula $-O-CO-(R^2-CO-)_m-O-$ derive from dimethyl esters or diphenyl esters of oxalic acid, of isophthalic acid, of phthalic acid, of adipic acid, or of sebacic acid.

11. (Original) The homo- or copolyoxymethylene as claimed in claim 7, wherein the structural elements of the formula $-O-CO-(R^2-CO-)_m-O-$ derive from oxybix(phthalic anhydride).

12. (Original) The homo- or copolyoxymethylene as claimed in claim 7, wherein the structural elements of the formula $-O-CO-(R^2-CO-)_m-O-$ derive from carbonyl N,N'-bis(caprolactamate).

13. (Previously Presented) The homo- or copolyoxymethylene as claimed in claim 1, whose melt index (MVR value, 190°C/2.16 kg/ISO 1133) is below 10 cm³/10 min.

14. (Withdrawn, Currently Amended) A process for the chain-extension of homo- or copolyoxymethylenes, encompassing the reaction of homo- or copolyoxymethylenes of the formula II with at least one chain-linking agent of the formula III



where A is a radical derived from a homo- or copolyoxymethylene,

R¹ is an alkylene radical having at least two carbon atoms, or a cycloalkylene radical,

R² is a direct carbon-carbon bond or an alkylene, cycloalkylene, arylene, or aralkylene radical,

R⁴ is a radical of the formulae formula $-OH$, $-O-R^5$, $-O-CO-R^6$, or $-O-R^1-OH$, where R¹ is defined at an earlier stage above,

R⁵ is an alkyl, cycloalkyl, aryl, or aralkyl radical,

R⁶ is hydrogen or an alkyl, cycloalkyl, aryl, or aralkyl radical,

m is 0 or 1, and

R^7 and R^8 , independently, of one another, are alkoxy, cycloalkoxy, aryloxy, aralkyloxy, or a lactam radical bonded by way of the nitrogen atom, or where, in the case where $m = 1$, R^7 and/or R^8 together with another carboxylic acid group of the radical R^2 form an anhydride or imide group.

15. (Withdrawn) The process as claimed in claim 14, wherein the reaction takes place in the presence of a catalyst which is a Lewis acid or is a Lewis base.

16. (Withdrawn) The process as claimed in claim 15, wherein the catalyst used comprises the alkali metal or alkaline earth metal salts of acetylacetonates and/or alkali metal alkoxides.

17. (Withdrawn) The process as claimed in claim 14, wherein the reaction takes place at temperatures of from 100 to 240°C and the reaction time is from 0.5 to 60 minutes.

18. (Withdrawn) The process as claimed in claim 14, wherein the amount used of homo- or copolyoxymethylene of the formula II, per mole of chain-linking agent of the formula III, is such that the content of the end groups $-O-R^1-OH$ present at the start of the chain-linkage reaction is in the range from one quarter of one mol to four mol.

19. (Withdrawn) The process as claimed in claim 14, wherein the reaction takes place at temperatures such that the reaction mixture is liquid, or such that a liquid phase forms in the reaction mixture.

20. (Withdrawn, Currently Amended) The process as claimed in claim 14, wherein, from a mixture of compounds of the formulae formula II and III, ~~if appropriate of~~ optionally a catalyst, and, optionally of other additives, a molded structure is produced and is heated in a stream of gas and/or in a vacuum for a period such that the desired

molecular weight increase has been achieved, the temperatures selected here being such that the reaction mixture is solid.

21. (Canceled)

22. (Previously Presented) The homo- or copolyoxymethylene as claimed in claim 7, wherein the structural elements of the formula $-O-CO-(R^2-CO-)_m-O-$ derive from dimethyl or diphenyl carbonate.

23. (Previously Presented) The homo- or copolyoxymethylene as claimed in claim 1, whose melt index (MVR value, 190°C/2.16 kg/ISO 1133) is below 2 cm³/10 min.

24. (Withdrawn) The process as claimed in claim 15, wherein the catalyst used comprises lithium acetylacetonate or sodium acetylacetonate, and/or sodium methoxide or lithium methoxide, and/or lithium halide and the reaction takes place at temperatures of from 150 to 220°C and the reaction time is from 0.5 to 60 minutes.

25. (Withdrawn, Currently Amended) A method for producing moldings, fibers, films, hoses, pipes, rods, or profiles which ~~comprising~~ comprises using the homo- or copolyoxymethylene as claimed in claim 1.